

USE AND DEVELOPMENT OF JUTE FIBRE IN REINFORCED CEMENT CONCRETE GRADE M40

Rahul R. Kshatriya¹, Vikas L. Kumavat², Mansi S. Kothalkar³, Chetan C. Chaudhary⁴, Roshan A. Khode⁵, Chetan N. Mahale⁶, Sanyogita S. Pawar⁷

¹Assistant Professor, Department of Civil Engineering, MCERC, Nashik (India) ^{2 to 7}UG Student Department of Civil Engineering, MCERC, Nashik (India)

ABSTRACT

As concrete is weak in tension and has brittle character. The concept of using fibres to improve the characteristics of construction materials is very old. Use of continuous reinforcement in concrete (reinforced concrete) increase strength and ductility, but requires careful placement and labour skill. Alternatively introduction to fibres in discrete form in plane and reinforced concrete may provide better solution. When concrete cracks, and randomly oriented fibres start functioning, arrest cracks formation and propagation, and thus improve strength and ductility. As India is one of the largest producers of jute, hence its potential application in many branches of engineering should be developed. In the present work the tensile, compressive, mechanical properties of jute fibre without modification and after modification with 0.5% alkali and 0.5% latex polymer has been modified by taking quantity of jute as 1% of cement. This modification of jute fibre improves tensile strength of Jute fiber also water absorption has been reduced. These properties are compared by taking tests on plain, with and without modification of jute fibre casting cube, cylinder and beams after curing of 7 days. From our project we had seen that there is considerable increase in strength of concrete by adding treated jute in concrete.

Keywords- Treatment of jute fiber, Use of jute in concrete, Use of jute in M40 grade concrete, Effect of jute in concrete.

I. INTRODUCTION

It is difficult to maintain strength of concrete and increase its durability, so addition of natural fibers is economical way to increase strength of concrete. The type of fibers currently been used include steel, glass, polymers, carbon and natural fibers. Economic considerations have restricted the use of carbon fibers in cementitious composites on a commercial level for their non ecological performance. Natural fibers have the potential to be used as reinforcement to overcome the inherent deficiencies in cementitious materials. Considerable researches are being done for use of reinforcing fibers like jute, bamboo, sisal, akwara, coconut husk, sugarcane bagasse in cement composites mostly in case of building materials. Use of natural fibers in a relatively brittle cement matrix has achieved considerable strength, and toughness of the composite. The durability of such fibers in a highly alkaline cement matrix must be taken into consideration by effective modifications. A specific chemical composition has to be chosen that can modify the fiber surface as well as strengthen the cement composite.



II. MATERIALS AND METHADOLOGY

2.1 Materials

Portland Pozzolona cement of M40 Grade was supplied by Ultratech Cement Pvt. Ltd. Locally available coarse aggregate (stone chips of size 0 - 20 mm) and sand were used for composite fabrication as per IS:456 -2002.Jute fibers of TD4 grade were collected from Jute Mill, Dindori, Nashik, India.

2.1.1 Jute



Photo 2.1 Jute fiber

Photo 2.2 Chopped jute fiber

India is one of the large jute producing country. Jute is an important bastfibre with a number of advantages. Jute has high specific properties, low density, less abrasive behavior to the processing equipment, good dimensional stability and harmlessness. Jute textile is a low cost eco-friendly product and is abundantly available, easy to transport and has superior drapability and moisture retention capacity. It is widely being used as a natural choice for plant mulching and rural road pavement construction. The biodegradable and low priced jute products merge with the soil after using providing nourishment to the soil. Being made of cellulose, on combustion, jute does not generate toxic gases.

Due to jute's low density combined with relatively stiff and strong behavior, the specific properties of jute fibre can compare to those of glass and some other fibres (Table 2.1).

Fibre	Density (g/cm ³)	Elongation (%)	Tensile Strength (MPa)	Young's Modulus (GPa)
Cotton	1.5-1.6	7.0-8.0	287-597	5.5-12.6
Jute	1.3	1.5-1.8	393-773	26.5
Flax	1.5	2.7-3.2	345-1035	27.6
Hemp	-	1.6	690	-
Ramie	_	3.6-3.8	400-938	61.4-128

Table 2.1 Machanical	proportion of n	atural fibras as com	parad to convention	1 rainforcing fibros
1 abie 2.1 Micchainea	properties of n	atural mores as com		al remotening mores

International Journal of Innovative Research in Science and Engineering



Vol. No.2, Issue 03, March 2016 www.ijirse.com

Sisal	1.5	2.0-2.5	511-635	9.4-22.0
Coir	1.2	30.0	175	4.0-6.0
Viscose(cord)	_	11.4	593	11.0

2.1.2Cement

Cement is material which generally use for bonding in concrete in construction industries. We used the Portland Pozzolanacement of 53 grade for our whole work. Before using some tests are carried on it. Some physical characteristics of cements are given in table 2.2

Table 2.2 Physical characteristics of cement

IS Code	Fineness (sq.m/kg) min	Soundn	ess by	Setting	; time	C	ompressiv	ve streng	ţth
		Lechatlier (mm) max	Auto clave Max (%)	I Initial (mts) min	Final (mts) Max	1 7 days Min Mpa	7 days Min Mpa	7days Min Mpa	2 8 days Min Mpa
(IS 269-	225	10	0.8	30	600	N	6	22	3

A) Test-Soundness of cement-

This test is performed to ascertain the soundness or unsoundnessofcement, which affects durability of the structure. The soundness of cement depends on its ingredients. Excess of lime and/or magnesium oxide present in the cement cause unsoundness .The test is designed to accelerate the expansion in the cement paste by application of heat.

Original distance between the pointers, $d_{1=}6mm$

Distance between the pointers after boiling, $d_2 = 10$ mm

As per IS 269-1987, the expansion of cement should not be more than 10mm Portland pozolona cement expansion of cement = 4mm there for cement is sound.

2.1.3 Fine aggregate

The river sand was used as fine aggregate conforming to the requirement of IS 383:1970. The river was washed and screened, to eliminate unwanted deleterious material and over size particles.

The test for determination of specific gravity was carried out. The surface dry aggregate were used for test. These properties of aggregate are necessary to decide proportions of the concrete mix.

Specific gravity of fine aggregate

Specific gravity (G) is defined as the ratio of weight of a given sample at standard temperature to the weight of equal volume of distilled water at the same temperature. Both weights are taken in air. Specific gravity of very coarse fraction (gravels, pebbles etc.) is calculated by using voluminometer and pycnometer is used to find the specific gravity of the particles of sand.

Table 2.3 Observation table



Sr. No.	Observation	1	2
1	Pychnometer no.	1	2
2	Mass of emptypychnometer (M_1) gm	650	650
3	Mass of emptypychnometer + Sand (M_2) gm	1190	1100
4	Mass of emptypychnometer + Sand + Distilled (M ₃) gm	1830	1835
5	Mass of emptypychnometer + Distilled (M_4) gm	1510	1520
6	Specific gravity =(M ₂ -M ₁)/[(M ₂ -M ₁)-(M ₃ - M ₄)]	2.45	3.33

The average specific gravity of sample is 2.8

2.1.4 Course aggregate

The coarse aggregate of 20mm from crushed ballast rock, conforming to IS 383:1970 were used. The aggregates were free from adherent coating, injurious amount of disintegrated pieces, alkali, vegetable matter and other deleterious substances. Care was taken that the aggregate do not contain high concentration of flaky, elongated shapes and organic impurities which might affect the strength or durability of concrete.

Aggregate impact value

Toughness is the property of material to resist the impact. The aggregate impact value gives a relative measure of resistance of an aggregate to sudden shock or impact. This resistance of aggregates is different from its resistance to gradually applied load. The impact test consist of giving the repeated impact to the smple of aggregates ,by a hammer weighing 14 kg and falling from a height of 380±5mm. The quantity of finer material passing through 2.36mm I.S sieve indicates the toughness of the sample.

Description	Sample 1
Total weight of dry sample taken = w_1 gm	780
Weight of portion passing 2.36 mm sieve = w_2gm	40
Aggregate impact value = $w_2/w_1 \ge 100 \%$	5.12

 Table 2.4 Record of observation for impact value

The mean aggregate impact value is 5.12% hence, the aggregate is classified as exceptionally strong.

2.1.5 Concrete



It is a mixture of sand, cement, water, course and fine aggregate. We carried above tests on materials and above values concrete mix design is made and proportion is as follows. Admixture is use as per suitability of conditions.

Concrete mix design: Grade M40

Water	Cement	Sand	Coarse aggregate
0.4 litre	1 Kg	1.44 Kg	2.35 Kg

2.2 Methodology

2.2.1 Problem statement

The properties of various fibers were identified and jute fiber is chosen as a natural fiber to replace by 1% weight of cement. And also it was treated with alkali and polymer latex such that the properties of jute fiber will change. And comparing in M40 grade plain cement concrete, raw jute cement concrete and modified jute cement concrete for compressive, split tensile and flexural strength.

2.2.2 Mixing process

The jute fiber reinforced concrete samples of mix design 1:1.44:2.35 (cement: sand: coarse aggregate, by weight) were fabricated by following process, for untreated and treated jute fiber reinforced concrete. Initially the chopped fibers of 6 cm length were immersed for 24 h in half of the total volume of water required for concrete preparation in a container. Next the half of the total amount of cement required was added to wet jute in that container with constant stirring to obtain jute-cement slurry. The jute cement slurry was then slowly poured into the pan-mixer with stirring provision and the pan-mixer was run for 2 min. Sand and rest of cement was mixed with this jute-cement slurry. The remaining amount of water, sand and aggregate was then added and the pan-mixer was run for further 5 min. The fresh cement concrete thus obtained was cast immediately in molds and allowed to setting.

All the specimens were demolded after 24 h of casting and water cured for 7 days respectively. At the specified date they were removed from water, surface dried and tested. Each test result represented the mean of at least three specimens.

2.2.3 Treatment on jute fiber

a) Treatment with alkali

The jute fibers were cut to ~6 cm of length and soaked in 0.5% (w/v) NaOH solution at ambient temperature maintaining a fiber to liquor ratio of 1:30. The fibers were kept immersed in the alkali solution for 24 h. The alkali treated fibers were then washed several times with distilled water to remove excess alkali from the fiber surface. The final pH was maintained at 7.0. The fibers were then air dried at room temperature for 24 h followed by oven drying at 55°C for 24 h.

b) Treatment with polymer latex

Commercially available aqueous emulsion of carboxylated styrene-butadiene copolymer based polymer latex was used to modify the jute fibers. The solid content of undiluted polymer latex was found to be 41%. Alkali



treated jute fibers were dipped into 0.5% (v/v) polymer latex for 24 h, maintaining a liquor ratio 1:30 at ambient condition. The fibers were then air dried at room temperature for 24 h followed by oven drying at 55°C for 24 h.

2.2.4 Test to be carried out on specimen for different composite

Sizes of specimen-

Cube- 150 mm X 150 mm X 150 mm.

Cylinder- Height- 300mm, Daimeter- 150mm

Beam- 700mm X 300mm X 150mm

Table 2.5 Test to be carried out on specimen for different composite for 7 days.

Sr.	Type of concrete composite	Test to be taken	Specimen			
No.	Type of concrete composite		Cube	Cylinder	Beam	
1	Plain cement concrete	Compression, tension	3	3	3	
2	Raw jute cement concrete	Compression, tension	3	3	3	
3	Treated jute cement concrete	Compression, tension	3	3	3	

III. RESULTS AND DISCUSSIONS

3.1 Introduction

Generally we taken compressive, split tensile and flexural strength on members. While the different tests are carried on cement, fine aggregate and course aggregate. The split tensile strength where obtain by following formula

2 X Loc

Tensile strength = (
$$\pi X Di$$

3.2 Test results of different specimen

Table 3.1 Test results of plain cement concrete

Mixture	Avg. Compressive strength(Mpa)	Avg. Split tensile strength(Mpa)	Load carried by beam in single point load test (KN)
Plain cement concrete	23.52	3.92	214.75
Raw jute cement concrete	27.53	4.22	216.79
Treated jute cement concrete	29.77	4.29	223.4



3.3 Graphs



Graph 3.1 Compressive strength results for cube after 7 days curing

From the graph, it is observed that the compressive strength of concrete is increased by 17.5% by adding raw jute and 26.5% by adding modified jute in concrete.





From the graph it is observed that the split tensile strength of concrete is increased by 7% by adding raw jute and 9% by adding modified jute in concrete.

International Journal of Innovative Research in Science and Engineering



Vol. No.2, Issue 03, March 2016 www.ijirse.com



3.3 Flexural strength results for beam after 7 days curing

From the graph it is observed that the flexural strength of concrete is increased by 1% by adding raw jute and 4% by adding modified jute in concrete.

IV. CONCLUSIONS

- 1) It was observed that when the jute is chemically treated then its degradation decreases.
- It was observed that when the raw jute is added in concrete by 1% weight of cement then the compressive strength of concrete cube increased by 17.5% and by adding modified jute compressive strength increase by 26.5%.
- 3) It was observed that when the raw jute is added in concrete by 1% weight of cement then the split tensile strength of concrete cylinder increased by 7% and by adding modified jute split tensile strength increase by 9%.
- 4) It was observed that when the raw jute is added in concrete by 1% weight of cement then the flexural strength of concrete cube increased by 1% and by adding modified jute flexural strength increase by 4%.
- 5)Hence, it is proved that modified replacement proportion is beneficial to use in practice as it gives workable concrete with more compressive, flexural and tensile strength.
- 6) It was observed that it is difficult to mix or spread jute in concrete also it is difficult to maintain water cement ration.

ACKNWOLEDGMENT

Authors are very thankful to Prof. U.P. Naik, Head, Department of Civil Engineering, MCERC, Nashik, India and Dr.G.K.Kharate, Principal, MCERC, Nashik, India for the support to the work.

REFERENCES

 B.VijayaRamnatha et.al. 'Evaluation of mechanical properties of abaca-jute-glass fibre reinforced epoxy Composite', Materials & Design., Vol. 51, p.357–366, October 2013.



- [2] Tara sen and H.N.Jagannath Reddy on 'strengthning of RC Beam inflexure using natural jute fibre textile reinforced composite system and its comparative study with CFRT and GFRP strengthning system.' International Journal of Sustainable Built Environment, Vol.2, p. 41–55, Jan 2013.
- [3] Prof.VeerapuramSridharan andAsst professor 'Optimization of Machinability of Polyester/Modified Jute Fabric Composite Using Grey Relational Analysis (GRA)'Procedia Engineering, Vol. 64, p. 1003–1012, 2013
- [4] Prof.BasudamAdhikari and Prof SubhasishBasuMajumder Materials Science Centre Indian Institute of Technology 'Development of jute fiber reinforced cement concrete composites',June 2011
- [5] Prof.S. Pravin Kumar on 'Effect of alkali treatment on jute fibre composite.',2007